

REINFORCED PAPER TAPE

WATER ACTIVATED TAPES

WP SERIES

Excellent tensile strength and optimum security for a range of hand-applied corrugate packaging applications.

WP Series reinforced paper tape contains a starch based water activated adhesive that provides an instant, aggressive bond to most corrugated surfaces. Fiberglass reinforcing filaments provide excellent tensile strength and optimum security for a range of packaging applications.

With 5 products to choose from, the WP Series has just the right strength for high-value, hand-applied, special-care manufacturing processes.

- > Range of adhesive strengths for light duty carton sealing to heavy duty sealing for large, bulky or heavy content cartons.
- > Starch based water activated adhesive provides an instant, aggressive bond to most corrugate.
- > Available with custom print message for delivery of goods without pilferage.
- > Paper and adhesive are 100% biodegradable.



Shurtape®

www.shurtape.com 1.888.442.TAPE

REINFORCED PAPER TAPE

WATER ACTIVATED TAPES



ALSO AVAILABLE

GP 100



General purpose reinforced paper tape. Starch based water activated adhesive with fiberglass reinforcing filaments.

- Light duty packaging applications
- Internal packaging for items placed in a secondary container
- Aggressive adhesive that becomes part of the box
- 100% recyclable/biodegradable

Paper Sheet (weight)	57 lbs
MD Tensile Strength	40 lbs/in width
CD Tensile Strength	26 lbs/in width

Conforms to ASTM D5749 Type II, Grade B Specification (replaced CID AA-1492B, CID AA-1671, PPP-T-45)

WP 100



General purpose reinforced paper tape. Starch based water activated adhesive with fiberglass reinforcing filaments.

- Light duty carton sealing
- Aggressive bond to most corrugate
- Excellent tensile strength and optimal security

Top Sheet (weight)	20 lbs
Bottom Sheet (weight)	24 lbs
MD Spacing	.625 in
MD Tensile Strength	55.7 lbs/in
CD Tensile Strength	23.4 lbs/in
MD Glass	110 Denier
MD Glass Spacing	5/8 in

WP 200



Production grade reinforced paper tape. Starch based water activated adhesive with fiberglass reinforcing filaments. Conforms to ASTM D5749-01 Type I, Class 2 Specification*

- Medium duty carton sealing for normal manufacturing and handling
- Aggressive bond to most corrugate
- Excellent tensile strength and optimal security

Top Sheet (weight)	24 lbs
Bottom Sheet (weight)	24 lbs
MD Spacing	.625 in
MD Tensile Strength	66.5 lbs/in
CD Tensile Strength	32 lbs/in
MD Glass	75/110 Denier
MD Glass Spacing	1/2 in

WP 240



Production grade custom surface printed reinforced paper tape. Starch based water activated adhesive with fiberglass reinforcing filaments. Conforms to ASTM D5749-01 Type I, Class 2 Specification*

- Medium duty carton sealing for normal manufacturing and handling
- Aggressive bond to most corrugate
- Excellent tensile strength and optimal security

Top Sheet (weight)	24 lbs
Bottom Sheet (weight)	24 lbs
MD Spacing	.5 in
MD Tensile Strength	66.5 lbs/in
CD Tensile Strength	32 lbs/in
MD Glass	75/110 Denier
MD Glass Spacing	1/2 in

WP 300



Performance grade reinforced paper tape. Starch based water activated adhesive with fiberglass and PET reinforcing filaments. Conforms to ASTM D5749-01 Type I, Class 2 Specification*

- Medium duty carton sealing for medium weight cartons
- Aggressive bond to most corrugate
- Excellent tensile strength and optimal security

Top Sheet (weight)	28 lbs
Bottom Sheet (weight)	24 lbs
MD Spacing	.5 in
MD Tensile Strength	70 lbs/in
CD Tensile Strength	36 lbs/in
MD Glass	75 Denier
MD Glass Spacing	1/2 in

WP 400



Heavy duty grade reinforced paper tape. Starch based water activated adhesive with fiberglass and PET reinforcing filaments. Conforms to ASTM D5749-01 Type I, Class 2 Specification*

- Heavy duty carton sealing for large, bulky or heavy content cartons
- Aggressive bond to most corrugate
- Excellent tensile strength and optimal security

Top Sheet (weight)	28 lbs
Bottom Sheet (weight)	24 lbs
MD Spacing	.5 in
MD Tensile Strength	80 lbs/in
CD Tensile Strength	40 lbs/in
MD Glass	75 Denier
MD Glass Spacing	1/2 in

* replaced CID AA-1492B, CID AA-1671, PPP-T-45, Rule 41